



T3-Gate ox (487)

2020-06-25

T3-904PCS, 50 min, 800C, dry oxidation

Per Wehlin



T3-Gate ox (487)

The last 12 values

Meas	Date	Ave	Range	Ave	Range	CL (target)	LCL x-bar	UC Lx-bar	UCL R-bar	
1	2020-06-25	4.5	0.00	4.50	0.00	5	4.5	5.5	1.5	T3-401G, 50 min
2	2020-02-06	4.8	0.32	4.76	0.32	5	4.5	5.5	1.5	Full boat
3	2019-11-27	4.8	0.95	4.77	0.95	5	4.5	5.5	1.5	Full boat
4	2019-11-21	4.9	0.13	4.89	0.13	5	4.5	5.5	1.5	Test wafer pos. 13
5	2019-11-14	4.9	0.14	4.85	0.14	5	4.5	5.5	1.5	Test wafer pos. 13
6	2019-11-13	4.8	0.15	4.84	0.15	5	4.5	5.5	1.5	Test wafer pos. 13
7	2019-11-12	4.9	0.14	4.86	0.139	5	4.5	5.5	1.5	Test wafer pos. 13
8	#NUM!	#NUM!	#NUM!							
9	#NUM!	#NUM!	#NUM!							
10	#NUM!	#NUM!	#NUM!							
11	#NUM!	#NUM!	#NUM!							
12	#NUM!	#NUM!	#NUM!							